

Laser Stripping of Aerospace Materials with Closed-Loop, Color-Recognition Control

**ASETS Defense 2009 Workshop
Sustainable Surface Engineering for
Aerospace and Defense
September 3, 2009**

**Robert Cargill, P.E.
General Lasertronics Corporation
San Jose, CA**

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 03 SEP 2009		2. REPORT TYPE		3. DATES COVERED 00-00-2009 to 00-00-2009	
4. TITLE AND SUBTITLE Laser Stripping of Aerospace Materials with Closed-Loop, Color-Recognition Control				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) General Lasertronics Corporation, 830 Jury Court, Suite 5, San Jose, CA, 95112				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES ASETSDefense 2009: Sustainable Surface Engineering for Aerospace and Defense Workshop, August 31 - September 3, 2009, Westminster, CO. Sponsored by SERDP/ESTCP.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 30	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

Laser Surface Preparation


Laser Ablation is the 21st Century Solution for Surface Cleaning and Surface Preparation:

- ***Demonstrated Zero Reduction in Material Properties***
- ***Negligible Environmental Impact and Abatement Costs***
- ***Installable as Workcell in Existing Production Facilities***
- ***Versatile Configurations with COTS–NDI Components***
- ***Demonstrated Reliability and Maintainability***
- ***True Closed-Loop Control Enables Manual or Robotic Positioning of Laser Workhead with Color Recognition***
- ***Cost Competitive with Current Decoating Technologies***
- ***The Only Laser Process that is FAA Approved for Commercial Aircraft***
- ***Successful Applications with Aluminum, Titanium, Steel and Composite Materials***

Photoablation Physics

Laser Ablation Process


- High-Intensity Radiant Heating ($10\text{-}30\text{ MW/cm}^2$)
- Very Short Duration ($0.2\text{ }\mu\text{sec}$),



- High Reflectance, so Heat Conduction is Small
 $\text{Time}_{\text{Vaporization}} \ll \text{Pulse duration} \ll \text{Time}_{\text{Conduction}}$

Surface Physics

Laser Scanning



- Coating removal from aerospace materials
 - Metal oxides and dust → Particulate ejecta
 - Oils and solvents → $\text{H}_2\text{O} + \text{CO}_2$
- Process Parameters Optimized to Clean and Deoxidize / Depassivate Substrate Surface

Surface Physics

Photoablation-Induced Texture




2024-T3 Alclad


“Golf Ball” texture
0.7 mm dia. x
0.008 mm depth in
0.05 mm-thick clad
layer

- Laser Parameters can be controlled in order to achieve desired surface finish effects




5201







2 mm




200 μm






100 μm



Material Temperature


Channel 1 Channel 2 Channel 3 Channel 4



- Temperature data at 4 depths during paint removal from 2024-T3 Al Clad
- Peaks match laser traverse events
- Ch. 4 impacted by thermal mass of doubler plate

Surface Temperature Estimates

Well below reference values



2024-T3 References


Annealing Temp
412.7 °C (775 ° F)


Solution Temp
493.3 °C (920 ° F)

Aging Temp
190.5 ° C (375 ° F)
for 8 -16 hours

S-N Fatigue Testing

GLC Fatigue Life Test for FAA - 2024-T3 Al-Clad







25 kV

30X

1 mm




2 mm



10 kV

20X


1 mm




10 kV

150X

200 μm





Surface Preparation for Bonding

Archive tests in support of Northrop F-18, F-35, B-2

- *Application: Pre-bond surface prep of titanium, aluminum, and composite surfaces*
- *Technique: Inter-laminar shear testing*
- *Results and conclusions:*
 - Bond strength equivalent to any other process
 - Trial-to-trial deviations almost zero
 - “Eliminates the human error factor in aircraft manufacture” - Doris Reis, Senior F-35 M&P Engineer
 - *Significant environmental impact reductions*
 - *Worker health and safety benefits*

Substrate Damage Studies

- **1989 - 1995 - US Navy, USAF**
- **1995 - 1999 - EPA/NASA/USAF: Burlingame**
 - “Very clean”
 - “Surface erosion - minimal”
- **More recent laser qualification programs**
 - AFRL - JGPP laser system qualifications
 - NCMS / CTMA rotorblade depaint evaluation
 - FAA/GLC MA4872 evaluation for commercial aircraft

GLC Material Tests for FAA

0.8 mm thick 2024 T3 Al Clad

<i>Parameter</i>	<i>Results</i>
<i>1. Peak surface temperature measured during stripping</i>	<i>130 to 150°C = no metallurgical impact</i>
<i>2. Microstructure analyzed before and after stripping</i>	<i>No change in properties</i>
<i>3. Microhardness measured before and after stripping</i>	<i>No change in properties</i>
<i>4. Microscopic surface texture measured after stripping</i>	<i>Texture effects in soft clad layer only</i>
<i>5. SAE MA-4872 fatigue life tested after 5 x laser stripping and repainting</i>	<i>Equivalent fatigue life <u>Process approved by FAA</u> <u>for use on commercial aircraft</u></i>

Environmental Impacts


- *Surface ejecta:*
 - *Metal oxide and dust particulate*
 - *Oxidized hydrocarbons (CO₂, H₂O)*
 - *Minimal un-oxidized hydrocarbons*
- *Integral fume extraction entrains all waste – no surface residuals*
- *HEPA filter for particle collection*
- *Vapor discharge below action levels*

Laser Ablation System

Equipment can be
rack, vehicle
mounted or fixed

Umbilical
Cable
(10-150+ feet)

Remote
Portable
Work Head



Units are modular and can be
separately sourced

Work head can be
handheld,
suction-mounted or
robot-mounted

Color Recognition of Layers

- *USAF & Lockheed Martin coordinated support of F-22 SBIR*
- *Goal: Replace hand sanding for LO coating maintenance*
- *Phase I - 2001, Phase II- 2002 - 2004, US Patent Application - 2004*




Figure 1 - Typical Stripping Requirements



Figure 3 - SBIR- Developed Workhead




Figure 2 - Actual Stripped Sample



Figure 1 - Current Rotor Blade Stripping at Cherry Point



Figure 2 - Example of Blade Sanding Damage




Figure 3 - Lasertronics Stripping Blade Sample





Figure 4 - Temperature during Laser Stripping

Defense Aerospace Installations



Automated rotorblade depaint,
Navy Fleet Readiness Center,
Cherry Point, NC



Hand-held system for
helicopter maintenance,
Patuxent River, MD

Reliability / Maintainability

- **Extended Service:**
 - April through September
 - 90 hrs/wk operation
 - >2000 hours
- **Reliability:**
 - Described as “Workhorse”
 - No optics cleaning required
 - No OEM service required
- **Maintainability:**
 - Field personnel completed all maintenance



Laser cleaning of thick corrosion layers from statuary on the City Hall of Philadelphia, PA



***830 Jury Court, Suite 5
San Jose, CA 95112
(408) 947-1181 — Fax: (408) 947-1666
Email: info@lasertronics.com
www.lasertronics.com***

